

DALLAS LABORATORIES, INC.

Consultants and Technologists
Chemical and Petroleum Chemists

P.O. BOX 152837, DALLAS, TEXAS 75315
1323 WALL ST, DALLAS, TEXAS 75215
PHONE 214/565-0593
FAX 214/565-1094

MEMBERS
AMERICAN CHEMICAL SOCIETY
ASTM INTERNATIONAL
AMERICAN SOCIETY OF MATERIALS

MEMBERS
AMERICAN NATIONAL STANDARDS INSTITUTE
AMERICAN SOCIETY FOR QUALITY CONTROL
FEDERATION OF SOCIETIES FOR COATINGS TECHNOLOGY

Submitted by: Aqua Sur Tech
2148 Trans-Canada Highway
Dorval, Quebec
Canada – H9P 2N4

Date: January 18, 2017

Attn: Michael Braeuel

Report No: 49239-1

REPORT

Lab Sample No.: One (1) Sample

49239-1 Tru Stain Top Coat

PROCEDURE

Samples are exposed as received to Xenon-Arc per ASTM G155 for 3,000 hours. Color was evaluated every 1,000 hours per ASTM D2244 with a Hunter Lab Ultra Scan XE using the Hunter L a b scale with the D65 illuminant and 10° angle.

RESULTS

49239-1

<u>Interval, hours</u>	<u>L</u>	<u>a</u>	<u>b</u>	<u>ΔE</u>
Initial	34.40	9.13	8.77	-
1,000	33.20	9.52	8.96	1.27
2,000	33.18	9.79	9.24	1.46
3,000	33.27	9.95	9.46	1.55

DALLAS LABORATORIES, INC.



Kevan W. Jones, Vice President

Analyst: KJ
KWJ: js